

Technical data sheet

PP CHIUSURA TRS. 90/RS3

PP CLEAR RECLOSABLE 90/RS3

Code: 131033

APPLICATION	This product can be used in the hygiene industry as closure of the packages of wet wipes. Specially designed to withstand repeated openings and closings and avoid the deterioration of the content. The adhesive is resistant to the various liquid components contained in the package. Specific for PET packaging. A careful evaluation of the functionality is necessary in own particular purpose.
	Clear, glossy polypropylene film, with Top Coating for printing.
FACE	Technical characteristics
MATERIAL	Thickness 92 µm
	Weight 83 gr/sqm

RS3: Acrylic, removable adhesive, solvent based with average initial tack and final adhesion. High resistance to sunlight and high cohesion. High resistance to moisture.

Minimum application temperature: +10°C Working temperature: -25°C +80°C

Food contact: not suitable

ADHESIVE Properties

Coat weight 22 +/- 3 gr/sqm FTM 12 Peel adhesion (180°) 20 min 4 - 7 N/inch FTM 1 - St. STEEL Peel adhesion (180°) 24 h. 5 - 8 N/inch FTM 1 - St. STEEL Quick stick 8 - 12 N/inch FTM 9 - St. STEEL Shear > 60 hours FTM 8 - St. STEEL

Super calendared, high density backing paper 73 gr/sqm. Constant thickness, good mechanical properties, suitable for automatic labelling. Good quality for optical scanning.

Technical characteristics

Thickness 63 µm ISO 534 LINER ISO 536 Weight 73 gr/sqm 63 N/cm ISO 1924 Tensile strength M.D. DIN 53147 Transparency 42 % Release 6 +/- 3 gr/inch FTM 3

Shelf life: 2 years when stored at 20-25°C, 40-50% relative humidity, in the original packaging. Don't expose the material at the direct sun light and to the heat sources.

This specification does not absolve users from performing its tests. The values indicated are the results of laboratory tests and under no circumstances must be taken to an absolute reference. It must therefore be deemed warranty or commitment. The user is solely responsible for all decisions about the use of the material. Roll Cover shall not be liable for any direct or indirect damages resulting from inappropriate use of the information contained in datasheets

Rev. May 2019