



**SQUEEZE PP TRS. 55/AT1/60 TC**  
SQUEEZE PP CLEAR 55/AT1/60 TC

**Code: 132003**

**APPLICATION**

Product ideally suitable for serialization of pharma packaging (Directive 2011/62/EU). The transparent label offers tamper evidence via ultra-strong (fibre tear) adhesive and conformability for sharp corners.

**FACE MATERIAL**

Clear, glossy conformable Polypropylene film with Top Coating for printing.

**Technical characteristics**

Thickness	55 µm
Weight	50 gr/sqm

**ADHESIVE**

**AT1:** Permanent, modified, acrylic adhesive, solvent based with high initial tack and high final adhesion. High cohesion.

Minimum application temperature: + 10°C  
Working temperature: -40°C +150°C,  
Food contact: not suitable

**Properties**

Coat weight	25 +/- 2 gr/sqm	FTM 12
Peel adhesion (180°) 20 min	> 12 N/inch	FTM 1 – St. STEEL
Peel adhesion (180°) 24 h.	> 15 N/inch	FTM 1 – St. STEEL
Quick stick	> 15 N/inch	FTM 9 – St. STEEL
Shear	> 15 hours	FTM 8 – St. STEEL

**LINER**

Super calendared, high density backing paper 60 gr/sqm. Constant thickness, good mechanical properties, suitable for automatic labelling. Good quality for optical scanning.

**Technical characteristics**

Thickness	53 µm	ISO 534
Weight	61 gr/sqm	ISO 536
Tensile strength M.D.	50 N/cm	ISO 1924
Transparency	47 %	DIN 53147
Release	8 +/- 4 gr/inch	FTM 3

Shelf life: 2 years when stored at 20-25°C, 40-50% relative humidity, in the original packaging. Don't expose the material at the direct sun light and to the heat sources.

*This specification does not absolve users from performing its tests. The values indicated are the results of laboratory tests and under no circumstances must be taken to an absolute reference. It must therefore be deemed warranty or commitment. The user is solely responsible for all decisions about the use of the material. Roll Cover shall not be liable for any direct or indirect damages resulting from inappropriate use of the information contained in datasheets*