

Weight

Release

Transparency

Tensile strength M.D.

Technical data sheet

Code: 160036

PP NERO SOFT TOUCH 23/60 TCX PP BLACK SOFT TOUCH 23/60 TCX

Film for lamination. Black, matt with "Soft Touch" effect. **APPLICATION** Black, matt Polypropylene film, with Top Coating for printing. **Technical characteristics FACE** Thickness 23 µm **MATERIAL** Weight 20 gr/sgm A2: Permanent acrylic adhesive, water based with low initial tack and low final adhesion. High resistance to sunlight and high cohesion. Minimum application temperature: + 10°C Working temperature: -40°C +150°C, Food contact: suitable for direct food contact, approved by ISEGA. **ADHESIVE Properties** 17 +/- 2 gr/sqm Coat weight FTM 12 Peel adhesion (180°) 20 min > 5 N/inch FTM 1 - St. STEEL Peel adhesion (180°) 24 h. > 7 N/inch FTM 1 - St. STEEL Quick stick > 5 N/inch FTM 9 - St. STEEL Shear > 80 hours FTM 8 - St. STEEL Super calendared, high density backing paper 60 gr/sqm. Constant thickness, good mechanical properties, suitable for automatic labelling. Good quality for optical scanning. **Technical characteristics** Thickness 53 µm ISO 534 **LINER**

Shelf life: 2 years when stored at 20-25°C, 40-50% relative humidity, in the original packaging. Don't expose the material at the direct sun light and to the heat sources.

61 gr/sqm 50 N/cm

6 +/- 3 gr/inch

47 %

ISO 536

FTM 3

ISO 1924

DIN 53147

This specification does not absolve users from performing its tests. The values indicated are the results of laboratory tests and under no circumstances must be taken to an absolute reference. It must therefore be deemed warranty or commitment. The user is solely responsible for all decisions about the use of the material. Roll Cover shall not be liable for any direct or indirect damages resulting from inappropriate use of the information contained in datasheets.